

Chemlon® 233 GVH

Teknor Apex Company (Chem Polymer) - Polyamide 6

Friday, June 30, 2017

General Information					
General					
Material Status	 Commercial: Active 				
Availability	 Asia Pacific 	• Europe	North America		
Filler / Reinforcement	Glass Fiber, 33% Filler by Weight				
Additive	Flame Retardant				
Features	Flame Retardant	 Good Stiffness 	High Strength		
Agency Ratings	• UL 94				
Appearance	Natural Color				
Forms	• Pellets				
Processing Method	Injection Molding				

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.60		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	21000	psi	ASTM D638	
Tensile Elongation (Break)	2.0	%	ASTM D638	
Flexural Modulus	1.10E+6	psi	ASTM D790	
Flexural Strength	32000	psi	ASTM D790	
Thermal	Nominal Value	Unit		
Melting Temperature	419	°F		
Flammability	Nominal Value	Unit	Test Method	
Flame Rating (0.06 in)	V-0		UL 94	

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 5/10/2012

¹ Typical properties: these are not to be construed as specifications.