

Sarlink® TPE EE-2268DN

Teknor Apex Company - Thermoplastic Polyolefin Elastomer

Friday, June 30, 2017

General Information

Product Description

Sarlink EE-2268DN is a medium impact, modified polypropylene used in transportation applications. Sarlink EE-2268DN is a high hardness grade and UV resistant. This grade can be processed by extrusion or injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Filled • High Hardness	• Light Stabilized • Low Flow	• Medium Density • Sunlight Resistant
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Exterior Trim • General Purpose	
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	245000	psi	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	2150	psi	
Flow : 100% Strain	2100	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	3160	psi	
Flow : Break	3640	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	320	%	
Flow : Break	140	%	
Tear Strength ³			ISO 34-1
Across Flow	1200	lbf/in	
Flow	800	lbf/in	
Compression Set ⁴			ISO 815
73°F, 22 hr	63	%	
158°F, 22 hr	86	%	
194°F, 70 hr	93	%	
257°F, 70 hr	100	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness ⁵			ISO 868
Shore D, 1 sec, Injection Molded	73		
Shore D, 5 sec, Injection Molded	69		
Shore D, 15 sec, Injection Molded	68		

上海松塑科技发展有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshs.com 联系电话: 021-58958519

Revision Date: 7/15/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE EE-2268DN

Teknor Apex Company - Thermoplastic Polyolefin Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁶			ISO 188
Across Flow : 230°F, 1008 hr	1.8	%	
Flow : 230°F, 1008 hr	9.0	%	
Across Flow : 100% Strain 230°F, 1008 hr	12	%	
Flow : 100% Strain 230°F, 1008 hr	68	%	
Across Flow : 257°F, 168 hr	-2.8	%	
Flow : 257°F, 168 hr	2.4	%	
Across Flow : 100% Strain 257°F, 168 hr	15	%	
Flow : 100% Strain 257°F, 168 hr	75	%	
Change in Tensile Strain at Break in Air ⁶			ISO 188
Across Flow : 230°F, 1008 hr	-58	%	
Flow : 230°F, 1008 hr	-7.2	%	
Across Flow : 257°F, 168 hr	-54	%	
Flow : 257°F, 168 hr	27	%	
Change in Shore Hardness in Air			ISO 188
Shore D, 230°F, 1008 hr ⁷	2.0		
Shore D, 230°F, 1008 hr ⁸	2.0		
Shore D, 230°F, 1008 hr ⁹	2.3		
Shore C, 257°F, 168 hr ⁷	1.1		
Shore D, 257°F, 168 hr ⁹	1.3		
Shore D, 257°F, 168 hr ⁸	1.2		

Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	560	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).



Revision Date: 7/15/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE EE-2268DN

Teknor Apex Company - Thermoplastic Polyolefin Elastomer

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	375 to 410	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ 24 hrs

⁶ Type 1

⁷ 1 sec

⁸ 5 sec

⁹ 15 sec

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 7/15/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.