

- Polypropylene

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Asia Pacific	• Latin America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Features	• Good Dimensional Stability	• High Heat Resistance	
	• Good Impact Resistance	• Medium Rigidity	
Uses	• Automotive Applications	• Furniture	• Housings
Appearance	• Colors Available		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow	8.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11600	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	667000	psi	ASTM D790
Flexural Strength	14500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.7	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, 0.126 in	316	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

**Teknor Apex Company
Corporate Headquarters**

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/21/2015

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.