

# Chemlon® 100 L

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Lubricant		
Features	• General Purpose	• Lubricated	
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/1.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.015 to 0.022	in/in	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	12000	psi	ASTM D638
Tensile Elongation (Yield)	5.0	%	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	405000	psi	ASTM D790
Flexural Strength	15800	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	425	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	190	°F	ASTM D648
Melting Temperature	495	°F	DSC
CLTE - Flow	3.9E-5	in/in/°F	ASTM D696
RTI Elec			UL 746
0.03 in	239	°F	
0.06 in	239	°F	
0.12 in	239	°F	
RTI Imp			UL 746
0.03 in	167	°F	
0.06 in	167	°F	
0.12 in	185	°F	
RTI Str			UL 746
0.03 in	203	°F	
0.06 in	203	°F	
0.12 in	203	°F	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms-cm	ASTM D257
Dielectric Strength (0.118 in)	460	V/mil	ASTM D149
Comparative Tracking Index (CTI)	600	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in)	V-2		UL 94

Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Chemlon® 100 L

## Teknor Apex Company (Chem Polymer) - Polyamide 66

Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Suggested Max Moisture	0.20	%
Suggested Max Regrind	25	%
Rear Temperature	465 to 490	°F
Middle Temperature	495 to 525	°F
Front Temperature	505 to 540	°F
Nozzle Temperature	505 to 535	°F
Processing (Melt) Temp	505 to 535	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

#### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.