

Chemlon® MD4

Teknor Apex Company (Chem Polymer) - Polyamide 6

Friday, June 30, 2017

General Information

Product Description

MD4 is an unfilled injection moulding grade of nylon 6. MD4 is heat stabilized and designed for the manufacture of components that will be exposed to elevated service temperatures.

General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• Heat Stabilizer
Features	• Heat Stabilized • High Heat Resistance
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Molding Shrinkage ²	1.2 to 2.0	--	%	Internal Method
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	3.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	450000	160000	psi	ISO 527-2
Tensile Stress (Yield)	10200	5800	psi	ISO 527-2
Tensile Strain (Break)	5.0	25	%	ISO 527-2
Flexural Modulus	435000	131000	psi	ISO 178
Flexural Stress ³	12300	3630	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	4.8	--	ft·lb/in ²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	374	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	203	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength (0.118 in)	360	410	V/mil	IEC 60243-1
Relative Permittivity (1 MHz)	3.50	4.00		IEC 60250
Dissipation Factor (1 MHz)	0.020	0.080		IEC 60250
Comparative Tracking Index	> 600	520		IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.06 in)	V-2			UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.06 in	1380		°F	
Oxygen Index	25		%	ISO 4589-2

上海松翰塑化科技有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.sh@hsj.com 联系电话: 021-58958579

Revision Date: 3/20/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Chemlon® MD4

Teknor Apex Company (Chem Polymer) - Polyamide 6

Processing Information

Injection	Dry Unit
Drying Temperature	176 °F
Drying Time	2.0 hr
Rear Temperature	464 to 500 °F
Middle Temperature	464 to 500 °F
Front Temperature	464 to 500 °F
Processing (Melt) Temp	< 572 °F
Mold Temperature	140 to 176 °F
Injection Rate	Fast
Screw Speed	50 to 200 rpm

Injection Notes

Back pressure: Low
Injection pressure: High

No drying is necessary unless the materials has been exposed to air for longer than three hours.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Mould shrinkage is significantly influenced by many factors including wall thickness, gating, component shape and moulding conditions. The range values stated were determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

³ At conventional deflection

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 3/20/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.