

Flexalloy® 9300-85

Teknor Apex Company - Polyvinyl Chloride Elastomer

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America		
Features	 Good Thermal Stability Oil Resistant	Recyclable MaterialUltra High Molecular Weight	Weather Resistant		
Uses	Coating ApplicationsHose	SealsTool/Tote Box	• Tubing		
Forms	• Pellets				
Processing Method	• Extrusion	Injection Molding			

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.28		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	2850	psi	ASTM D638		
Tensile Elongation (Break)	370	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	85		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	221	°F	ASTM D794		
Brittleness Temperature	-38.2	°F	ASTM D746		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.