

Flexalloy® OR 9800-55

Teknor Apex Company - Polyvinyl Chloride Elastomer

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Oil Resistant • Ultra High Molecular Weight		
Uses	• Footwear • Gaskets • Hose	• Power/Other Tools • Seals • Tool/Tote Box	• Tubing • Wire & Cable Applications
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1030	psi	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Compression Set (158°F, 22 hr)	71	%	ASTM D395
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	54		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	194	°F	ASTM D794
Brittleness Temperature	-59.8	°F	ASTM D746

Additional Information

Elongation Retention , Oil Immersion, ASTM #3 oil, 125°C, 7 days: 80%
 Tensile Strength Retention , Oil Immersion, ASTM #3 oil, 125°C, 7 days: 166%
 Swell, Oil Immersion, ASTM #3 oil, 125°C, 7 days: -4.3%
 Dynamic Heat Stability, 205°C: >60 min

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
 Fax: 401-725-8095
 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
 Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013