🕐 TEKNOR APEX

Flexalloy[®] OR 9800-60

Teknor Apex Company - Polyvinyl Chloride Elastomer

Friday, June 30, 2017

General Information

Material Status	Commercial: Active		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Features	Oil Resistant	Ultra High Molecular Weight	
Uses	FootwearGasketsHose	Power/Other ToolsSealsTool/Tote Box	TubingWire & Cable Applications
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.14		ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	1210	psi	ASTM D638	
Tensile Elongation (Break)	320	%	ASTM D638	
Elastomers	Nominal Value	Unit	Test Method	
Compression Set (158°F, 22 hr)	42	%	ASTM D395	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	59		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	194	°F	ASTM D794	
Brittleness Temperature	-59.8	°F	ASTM D746	
Additional Information				

Elongation Retention, Oil Immersion, ASTM #3 oil, 125°C, 7 days: 82% Tensile Strength Retention, Oil Immersion, ASTM #3 oil, 125°C, 7 days: 150% Swell, Oil Immersion, ASTM #3 oil, 125°C, 7 days: -3.5% Dynamic Heat Stability, 205°C: >60 min

Notes

¹ Typical properties: these are not to be construed as specifications.

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864 Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

Teknor Apex U.K. Ltd.

etpsales@teknorapex.co.uk

info@teknorapex.com

Teknor Apex Company

Corporate Headquarters



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.