

APEX® 94-A0098A-80

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

General

| | | | |
|-------------------|------------------------------------------|-----------------------------|-------------------|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Features | • General Purpose | | |
| Uses | • Appliance Components | • Furniture | • General Purpose |
| Appearance | • Natural Color | • Opaque | |
| Forms | • Pellets | | |
| Processing Method | • Injection Molding | | |

ASTM & ISO Properties¹

| Physical | Nominal Value | Unit | Test Method |
|--------------------------------------|---------------|------|-------------|
| Specific Gravity | 1.30 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 2350 | psi | ASTM D638 |
| Tensile Elongation (Break) | 350 | % | ASTM D638 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 80 | | ASTM D2240 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -18.4 | °F | ASTM D746 |

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013