😰 TEKNOR APEX

APEX[®] 3300-70NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

| General | | | | |
|-------------------|---|--|---------------|--|
| Material Status | Commercial: Active | | | |
| Availability | Africa & Middle East Asia Pacific | EuropeLatin America | North America | |
| Additive | Plasticizer | | | |
| Features | DEHP Plasticizer | Ethylene Oxide Sterilizable | | |
| Uses | Food Service Applications | Medical/Healthcare Applications Tubing | | |
| Appearance | Clear/Transparent | | | |
| Forms | Pellets | | | |
| Processing Method | Extrusion | | | |

| ASTM & ISO Properties ¹ | | | | |
|--------------------------------------|---------------|------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.19 | | ASTM D792 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (100% Strain) | 750 | psi | ASTM D638 | |
| Tensile Strength (Break) | 1980 | psi | ASTM D638 | |
| Tensile Elongation (Break) | 460 | % | ASTM D638 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore A, 15 sec) | 70 | | ASTM D2240 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Brittleness Temperature | -34.6 | °F | ASTM D746 | |

Processing Information Extrusion Nominal Value Unit Melt Temperature 345 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Toll Free (U.S. only) 800-556-3864

Phone: 401-725-8000 Fax: 401-725-8095 Phone: (44) 121-665-2100 Fax: (44) 121-544-5530 etpsales@teknorapex.co.uk

Oldbury, West Midlands B69 4NH England

Teknor Apex U.K. Ltd.

Tat Bank Road

info@teknorapex.com



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with selfer's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.