

Teknor Apex Company - Polyolefin

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	Africa & Middle East Asia Pacific Europe Latin America	North America		
Additive	Flame Retardant			
Features	Flame Retardant Halogen Free			
Uses	Communication Wire Jacketing  Electronic Cable	e Jacketing • Security Cable Jacketing		
Agency Ratings	ICEA Unspecified Rating IEC Unspecified	d Rating • UL QMTM2		
RoHS Compliance	RoHS Compliant			
Appearance	Opaque			
Forms	Pellets			
Processing Method	Extrusion			

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.32		ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/10.0 kg)	15	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2000	psi	ASTM D638	
Tensile Elongation (Break)	270	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D, 10 sec)	46		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-58.0	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	6.4E+14	ohms∙cm	ASTM D257	
Dielectric Constant (1 kHz)	3.40		ASTM D150	
Dissipation Factor (1 kHz)	2.0E-3		ASTM D150	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	34	%	ASTM D2863	
Additional Information				

**Additional Information** 

Ultimate Elongation Retained, UL 1581, Oven Aged, 7 days, 100°C: 86 % Tensile Strength Retained, UL 1581, Oven Aged, 7 days, 100°C: 106 % Cone Calorimeter @ 50 kW/m<sup>2</sup>, Peak Heat Release Rate: 266 kW/m<sup>2</sup> Cone Calorimeter @ 50 kW/m<sup>2</sup>, Total Heat Released: 195 MJ/m<sup>2</sup> Cone Calorimeter @ 50 kW/m<sup>2</sup>, Peak Smoke: 2 1/m Cone Calorimeter @ 50 kW/m<sup>2</sup>, Time to Sustained Ignition: 106 sec

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.



Revision Date: 4/22/2015

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with selfer's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

## HFFR 2005PC Teknor Apex Company - Polyolefin

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 4/22/2015

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.