

# Sarlink® TPV 3460N

Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, June 29, 2017

## General Information

### Product Description

Sarlink TPV 3460N is a high performance thermoplastic vulcanizate used in a variety of automotive, consumer and industrial applications. Sarlink TPV 3460N is a low hardness, low density, RoHS compliant grade suitable for injection molding, blow molding and extrusion.

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Chemical Resistant • General Purpose • Good Adhesion	• High Heat Resistance • Low Density • Low Hardness	• Low Specific Gravity
Uses	• Fittings • General Purpose	• Piping • Potable Water Applications	
Agency Ratings	• NSF STD-61		
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Blow Molding • Extrusion	• Injection Molding • Pipe Extrusion	

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950		ASTM D792
Density	0.950	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	348	psi	
Flow : 100% Strain	421	psi	
Tensile Stress			ISO 37
Across Flow : 100% Strain	348	psi	
Flow : 100% Strain	421	psi	
Tensile Strength			ASTM D412
Across Flow : Yield	899	psi	
Flow : Yield	609	psi	
Tensile Stress			ISO 37
Across Flow : Break	899	psi	
Flow : Break	609	psi	
Tensile Elongation			ASTM D412
Across Flow : Break	650	%	
Flow : Break	350	%	
Tensile Elongation			ISO 37
Across Flow : Break	650	%	
Flow : Break	350	%	
Tear Strength - Across Flow <sup>2</sup>	182	lbf/in	ASTM D624
Tear Strength - Across Flow	180	lbf/in	ISO 34-1

上海松翰塑化科技有限公司  
 TEKNOR APEX 特诺尔爱佩斯 一级分销商  
 teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 5/9/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 3460N

## Teknor Apex Company - Thermoplastic Vulcanizate

<b>Elastomers</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Compression Set			ASTM D395B
73°F, 22 hr	23	%	
158°F, 22 hr	38	%	
212°F, 22 hr	41	%	
Compression Set			ISO 815
73°F, 22 hr	23	%	
158°F, 22 hr	38	%	
257°F, 70 hr	41	%	
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	62		
Shore A, 5 sec, Injection Molded	66		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	62		
Shore A, 5 sec, Injection Molded	66		
<b>Aging</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Change in Tensile Strength in Air - Across Flow			ASTM D573
275°F, 1000 hr	-4.0	%	
100% Strain, 275°F, 1000 hr	3.0	%	
302°F, 168 hr	-1.0	%	
100% Strain, 302°F, 168 hr	7.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
275°F, 1000 hr	-4.0	%	
100% Strain 275°F, 1000 hr	3.0	%	
302°F, 168 hr	-1.0	%	
100% Strain 302°F, 168 hr	7.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
275°F, 1000 hr	-5.0	%	
302°F, 168 hr	-11	%	
Change in Tensile Strain at Break in Air			ISO 188
275°F, 1000 hr	-5.0	%	
302°F, 168 hr	-11	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 275°F, 1000 hr	2.0		
Shore A, 302°F, 168 hr	3.0		
Change in Shore Hardness in Air			ISO 188
Shore A, 275°F, 1000 hr	2.0		
Shore A, 302°F, 168 hr	3.0		
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	120	%	ASTM D471
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	120	%	ISO 1817
<b>Additional Information</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Apparent Shear Viscosity - Capillary, @ 206/s			
392°F	310	Pa·s	ISO 11443
392°F	310	Pa·s	ASTM D3835

Revision Date: 5/9/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 3460N

## Teknor Apex Company - Thermoplastic Vulcanizate

### Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0	hr
Rear Temperature	350 to 420	°F
Middle Temperature	350 to 420	°F
Front Temperature	350 to 420	°F
Nozzle Temperature	370 to 430	°F
Processing (Melt) Temp	360 to 430	°F
Mold Temperature	50 to 150	°F
Back Pressure	10.0 to 150	psi
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	

Extrusion	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	360 to 400	°F
Cylinder Zone 2 Temp.	360 to 400	°F
Cylinder Zone 3 Temp.	370 to 410	°F
Cylinder Zone 4 Temp.	370 to 410	°F
Melt Temperature	380 to 420	°F
Die Temperature	380 to 420	°F
Take-Off Roll	70 to 120	°F

### Extrusion Notes

Screen Pack: 20 to 60 mesh  
Screw: 3:1 Compression Ratio

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C

#### Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

#### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 5/9/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.