

APEX® 93-A0591C-97

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Uses	• Transportation Wire Insulation		
Wire Types	• GPT		
Agency Ratings	• SAE J1128		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2670	psi	ASTM D638
Tensile Elongation (Break)	290	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	72		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-0.400	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863

Additional Information

Temperature Rating: 105 °C
 Ultimate Elongation Retained, UL 1581, Oven Aged, 7 days, 136°C: 93 %
 Tensile Strength Retained, UL 1581, Oven Aged, 7 days, 136°C: 95 %

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	375	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
 Engineered Thermoplastics (Chem Polymer)
 505 Central Avenue
 Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
 Fax: 401-725-8095
 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
 Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.