

APEX® CXFR 2001-84

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information				
General				
Material Status	 Commercial: Active 			
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America	
Features	Flame Retardant			
Uses	Cable Jacketing	Coaxial Cable Jacketing	g	
Agency Ratings	• UL 444	• UL 62		
RoHS Compliance	 RoHS Compliant 			
Appearance	 Opaque 			
Forms	• Pellets			
Processing Method	 Extrusion 			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.42		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2200	psi	ASTM D638	
Tensile Elongation (Break)	310	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	84		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	176	°F	ASTM D794	
Brittleness Temperature	-7.60	°F	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	29	%	ASTM D2863	

Additional Information

Temperature Rating: 75 °C

UL Sunlight Resistance Recognition: No

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	360 °F		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.