

APEX® 240

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America		
Features	Flame Retardant	 Low to No Migration 			
Uses	Communication Wire Jacket	• Telephone Retractile Cord Jacketing			
Agency Ratings	NEC Article 725				
RoHS Compliance	RoHS Compliant				
Appearance	 Clear/Transparent 				
Forms	• Pellets				
Processing Method	 Extrusion 				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.24		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2500	psi	ASTM D638	
Tensile Elongation (Break)	400	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	75		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	176	°F	ASTM D794	
Brittleness Temperature	-18.4	°F	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	28	%	ASTM D2863	
A -1-11411 1 f 41				

Additional Information

High quality

Coil cord jackets

Temperature Rating: 80 °C

UL Sunlight Resistance Recognition: No

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	350 °F		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)

505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松静理化科技有限公司 上海松静理化科技有限公销商 TEKNOR APEX 特诺尔爱佩斯 TEKNOR APEX 特诺尔爱佩斯 teknorapex.shshsj.com 联系电流: 021-58958519

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.