

APEX® 7500-80

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

| General Information | | | | | | |
|---------------------|---|--|---------------|--|--|--|
| General | | | | | | |
| Material Status | Commercial: Active | | | | | |
| Availability | Africa & Middle EastAsia Pacific | EuropeLatin America | North America | | | |
| Features | High Heat Resistance | | | | | |
| Uses | ConnectorsGrommets | PlugsStrain Reliefs | | | | |
| Wire Types | Molded Components | | | | | |
| Agency Ratings | • UL QMFZ2 | | | | | |
| RoHS Compliance | RoHS Compliant | | | | | |
| Appearance | Clear/Transparent | | | | | |
| Forms | • Pellets | | | | | |
| Processing Method | Injection Molding | | | | | |

| ASTM & ISO Properties 1 | | | | | |
|--------------------------------------|----------------|-------|-------------|--|--|
| Physical | Nominal Value | Unit | Test Method | | |
| Specific Gravity | 1.21 | | ASTM D792 | | |
| Molding Shrinkage - Flow | 0.010 to 0.012 | in/in | ASTM D955 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength (Break) | 2250 | psi | ASTM D638 | | |
| Tensile Elongation (Break) | 380 | % | ASTM D638 | | |
| Hardness | Nominal Value | Unit | Test Method | | |
| Durometer Hardness (Shore A, 15 sec) | 80 | | ASTM D2240 | | |
| Thermal | Nominal Value | Unit | Test Method | | |
| Continuous Use Temperature | 221 | °F | ASTM D794 | | |
| Brittleness Temperature | -41.8 | °F | ASTM D746 | | |
| RTI Elec (0.06 in) | 122 | °F | UL 746 | | |
| RTI Imp (0.06 in) | 122 | °F | UL 746 | | |
| RTI Str (0.06 in) | 122 | °F | UL 746 | | |
| Flammability | Nominal Value | Unit | Test Method | | |
| Flame Rating (0.06 in) | НВ | | UL 94 | | |
| Oxygen Index | 22 | % | ASTM D2863 | | |

| Processing Information |
|------------------------|

 Injection
 Nominal Value
 Unit

 Processing (Melt) Temp
 355 °F

Notes

Temperature Rating: 105 °C

¹ Typical properties: these are not to be construed as specifications.

355 °F
355 °F
355 °F
TEKNOR APEX 特護不足順期 021-58958519
TEKNOR APEX 特護不足順 021-58958519
Teknorapex.shshsj.com 麻麻麻麻: 021-58958519

Revision Date: 12/12/2013

APEX® 7500-80

Teknor Apex Company - Flexible Polyvinyl Chloride

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013