

Sarlink® TPV X5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, June 29, 2017

General Information

Product Description

The Sarlink TPV 5700B series are highly engineered extrusion-grade thermoplastic vulcanizates with outstanding UV stability designed for demanding automotive interior and exterior sealing applications, including glass run channels, waistbelts, weather strips, seals and other profiles. Sarlink TPV X5740DB is a high hardness, medium density, high performance grade with low fogging and excellent color retention and elastic properties.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Chemical Resistant • High Hardness • High Heat Resistance	• High Tensile Strength • Low Compression Set • Medium Density	• Resilient • UV Resistant
Uses	• Automotive Applications • Belts/Belt Repair	• Profiles • Rubber Replacement	• Seals • Weatherstripping
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• BMW Mini/BMW Unspecified Color: Black • GM GMW15812 Type 9 Color: Black • PSA Peugeot-Citroën B62 0300 version G Color: Black • TOYOTA TSM 5746G-1 Color: Black		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Blow Molding • Extrusion	• Injection Molding • Profile Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960		ASTM D792
Density	0.960	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	1310	psi	
Flow : 100% Strain	1930	psi	
Tensile Stress			ISO 37
Across Flow : 100% Strain	1310	psi	
Flow : 100% Strain	1930	psi	
Tensile Strength			ASTM D412
Across Flow : Break	2760	psi	
Flow : Break	2610	psi	
Tensile Stress			ISO 37
Across Flow : Break	2760	psi	
Flow : Break	2610	psi	
Tensile Elongation			ASTM D412
Across Flow : Break	640	%	
Flow : Break	490	%	
Tensile Elongation			ISO 37
Across Flow : Break	640	%	
Flow : Break	490	%	

上海松翰塑化科技有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshs.com 联系电话: 021-58958519

Revision Date: 6/1/2016

Sarlink® TPV X5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tear Strength - Across Flow	500	lbf/in	ASTM D624
Tear Strength - Across Flow ²	500	lbf/in	ISO 34-1
Compression Set			ASTM D395
73°F, 22 hr	46	%	
158°F, 22 hr	58	%	
257°F, 70 hr	80	%	
Compression Set			ISO 815
73°F, 22 hr	46	%	
158°F, 22 hr	58	%	
257°F, 70 hr	80	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 5 sec, Extruded	38		
Shore D, 5 sec, Injection Molded	40		
Shore Hardness			ISO 868
Shore D, 5 sec, Extruded	38		
Shore D, 5 sec, Injection Molded	40		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
275°F, 1000 hr	-20	%	
100% Strain, 275°F, 1000 hr	9.0	%	
302°F, 168 hr	-22	%	
100% Strain, 302°F, 168 hr	5.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
275°F, 1000 hr	-20	%	
100% Strain 275°F, 1000 hr	9.0	%	
302°F, 168 hr	-22	%	
100% Strain 302°F, 168 hr	5.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
275°F, 1000 hr	-25	%	
302°F, 168 hr	-25	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
275°F, 1000 hr	-25	%	
302°F, 168 hr	-25	%	
Change in Durometer Hardness in Air			ASTM D573
Shore D, 275°F, 1000 hr	3.0		
Shore D, 302°F, 168 hr	3.0		
Change in Shore Hardness in Air			ISO 188
Shore D, 275°F, 1000 hr	3.0		
Shore D, 302°F, 168 hr	3.0		
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	47	%	ASTM D471
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	47	%	ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
392°F	400	Pa·s	ISO 11443
392°F	400	Pa·s	ASTM D3835

上海松翱塑化科技有限公司
 TEKNOR APEX 特诺小爱佩斯一级分销商
 teknorapex.shsh.com 联系电话: 021-58958858

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV X5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0	hr
Rear Temperature	350 to 420	°F
Middle Temperature	350 to 420	°F
Front Temperature	350 to 420	°F
Nozzle Temperature	370 to 430	°F
Processing (Melt) Temp	360 to 430	°F
Mold Temperature	50 to 150	°F
Back Pressure	10.0 to 150	psi
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	

Extrusion	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	360 to 400	°F
Cylinder Zone 2 Temp.	360 to 400	°F
Cylinder Zone 3 Temp.	370 to 410	°F
Cylinder Zone 4 Temp.	370 to 410	°F
Melt Temperature	380 to 420	°F
Die Temperature	380 to 420	°F
Take-Off Roll	70 to 120	°F

Extrusion Notes

Screen Pack: 20 to 60 mesh
Screw: 3:1 Compression Ratio

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.