🚯 TEKNOR APEX

Fireguard® 910-NL1 Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

Material Status	Commercial: Active		
Availability	 Africa & Middle East Asia Pacific	 Europe Latin America	North America
Features	Flame Retardant	Low Smoke Emission	
Uses	Insulation	Plenum Cable Jacketing	
Wire Types	• CL2P	CMP	MPP
	• CL3P	• FPLP	OFNP
Agency Ratings	NEC Article 725	NEC Article 800	• UL 1651
	NEC Article 760	• UL 13	• UL 444
	NEC Article 770	• UL 1424	UL QMTM2
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Extrusion		

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.59		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2550	psi	ASTM D638	
Tensile Elongation (Break)	200	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore C	92			
Shore C, 10 sec	85			
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	167	°F	ASTM D794	
Brittleness Temperature	21.2	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Strength	840	V/mil	ASTM D149	
Dielectric Constant			ASTM D150	
1 kHz	4.67			
1 MHz	3.62			
Dissipation Factor			ASTM D150	
1 kHz	0.080			
1 MHz	0.035			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	0.080 0.035 Nominal Value 45. Lite KNOR APEX H TEKNOR APEX H TEKNOR APEX H	% 科技有[新 請 示 爱佩斯	及分前ASTM D2863 30-58958519 21-58958519	

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Fireguard® 910-NL1 Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Av.Sp. Extinction Area: 273 m²/kg Avg. Heat of Combustion: 13.8 MJ/kg Avg. Heat Rel. Rate: 64 kw/m² Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 50 Kayeness ACR, 370°F, 1000 sec-1: 258 PA-sec

Peak Heat Rel. Rate: 119 kw/m² Peak Smoke: 2.3 Specific Gravity, ASTM D792: 1.57 to 1.61 sp gr 23/23°C TA Six Digit Description: 108-124 Total Heat Rel'd: 78 MJ/m²

Processing Information

Extrusion

Melt Temperature

385 °F

Nominal Value Unit

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

Teknor Apex U.K. Ltd. Tat Bank Road

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Oldbury, West Midlands B69 4NH England Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.