

# Fireguard® 910-A10B-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Low Smoke Emission	
Uses	• Insulation	• Plenum Cable Jacketing	
Wire Types	• CL2P • CL3P	• CMP • FPLP	• MPP • OFNP
Agency Ratings	• NEC Article 725 • NEC Article 760 • NEC Article 770	• NEC Article 800 • UL 13 • UL 1424	• UL 1651 • UL 444 • UL QMTM2
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2280	psi	ASTM D638
Tensile Elongation (Break)	220	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore C	88		
Shore C, 10 sec	82		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	5.00	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	4.94		
1 MHz	3.65		
Dissipation Factor			ASTM D150
1 kHz	0.083		
1 MHz	0.033		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	39	%	ASTM D2863

### Additional Information

Av.Sp. Extinction Area: 461 m<sup>2</sup>/kg  
 Avg. Heat of Combustion: 13.9 MJ/kg  
 Avg. Heat Rel. Rate: 59 kw/m<sup>2</sup>  
 Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 58  
 Peak Heat Rel. Rate: 111 kw/m<sup>2</sup>  
 Peak Smoke: 2.5  
 Kayeness ACR, 370°F, 1000 sec-1: 268 PA-sec  
 Specific Gravity, ASTM D792: 1.55 to 1.59 sp gr 23/23°C  
 TA Six Digit Description: 108-443  
 Total Heat Rel'd: 81 MJ/m<sup>2</sup>

上海松翰塑化科技有限公司  
 TEKNOR APEX 特诺尔爱佩斯 一级分销商  
 teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Fireguard® 910-A10B-NL1

## Teknor Apex Company - Flexible Polyvinyl Chloride

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

---

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*

505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

#### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松翰塑化科技有限公司  
TEKNOR APEX 特诺尔爱佩斯 一级分销商  
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.