

Fireguard® 910L16-C6-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

Conoral	General II	nformation		
General	Common anni alv. A ativ ca			
Material Status	Commercial: Active	F		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America		North America
Features	 Flame Retardant 	 Low Smoke Emission 	on	
Uses	 Plenum Cable Jacketing 			
Wire Types	• CL2P • CL3P	• CMP • FPLP		• MPP • OFNP
Agency Ratings	NEC Article 725NEC Article 760NEC Article 770	NEC Article 800UL 13UL 1424		UL 1651UL 444UL QMTM2
RoHS Compliance	RoHS Compliant			
Appearance	Opaque			
Forms	Pellets			
Processing Method	• Extrusion			
	ASTM & ISC	D Properties ¹		
Physical		Nominal Value	Unit	Test Method
Specific Gravity		1.63		ASTM D792
Mechanical		Nominal Value	Unit	Test Method
Tensile Strength (Break)		2200	psi	ASTM D638
Tensile Elongation (Break)		200	%	ASTM D638
Hardness		Nominal Value	Unit	Test Method
Durometer Hardness				ASTM D2240
Shore C		88		
Shore C, 10 sec		81		
Thermal		Nominal Value	Unit	Test Method
Continuous Use Temperature		167	°F	ASTM D794
Brittleness Temperature		-4.00	°F	ASTM D746
Electrical		Nominal Value	Unit	Test Method
Dielectric Constant				ASTM D150
1 kHz		4.75		
1 MHz		3.74		
Dissipation Factor				ASTM D150
1 kHz		0.063		
1 MHz		0.037		
Flammability		Nominal Value	Unit	Test Method
Oxygen Index		上海松前理化 TEKNOR APEX 特 teknorapex.shshsj.co	% 科技有 料液不是佩斯 所以来源域:0	Test Method RASTM D2863 21-58958519

Revision Date: 12/12/2013

Fireguard® 910L16-C6-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Av.Sp. Extinction Area: 262 m²/kg Avg. Heat of Combustion: 12.54 MJ/kg

Avg. Heat Rel. Rate: 67 kw/m²

Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 44 Kayeness ACR, 370°F, 1000 sec-1: 424 PA-sec

Peak Heat Rel. Rate: 111 kw/m²

Peak Smoke: 1.1 1/m

TA Six Digit Description: 0115306 Total Heat Rel'd: 62 MJ/m²

Processing Information

Extrusion Nominal Value Unit

Melt Temperature 380 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)

505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013