

APEX® 80873

Teknor Apex Company - Semi-Rigid Polyvinyl Chloride

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Semi Rigid		
Uses	• Automotive Electronics	• Insulation	
Wire Types	• AWM • GPT • TFFN	• THHN • THW • THWN	• TW
Agency Ratings	• SAE J1128 • UL 1063	• UL 1581 • UL 83	
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	3550	psi	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	83		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	8.60	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	3.59		
1 MHz	2.89		
Dissipation Factor			ASTM D150
1 kHz	0.061		
1 MHz	0.035		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.



Revision Date: 12/12/2013

APEX® 80873

Teknor Apex Company - Semi-Rigid Polyvinyl Chloride

Teknor Apex Company
Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.