

# **APEX® 84468**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

| General Information |   |  |               |  |  |
|---------------------|---|--|---------------|--|--|
| General             |   |  |               |  |  |
| Material Status     | Commercial: Active  |  |               |  |  |
| Availability        | <ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul> | North America |  |  |
| Features            | Flame Retardant   | <ul> <li>UV Resistant</li> </ul>               |               |  |  |
| Uses                | <ul> <li>Cable Jacketing</li> </ul>                               | <ul> <li>Insulation</li> </ul>                 |               |  |  |
| Wire Types          | • AWM   |  |               |  |  |
| Agency Ratings      | • UL 1063   | • UL 1581                                      | • UL 62       |  |  |
| RoHS Compliance     | <ul> <li>RoHS Compliant</li> </ul>                                |  |               |  |  |
| Appearance          | • Opaque  |  |               |  |  |
| Forms               | • Pellets   |  |               |  |  |

| ASTM & ISO Properties 1              |               |      |             |  |  |
|--------------------------------------|---------------|------|-------------|--|--|
| Physical                             | Nominal Value | Unit | Test Method |  |  |
| Specific Gravity                     | 1.35          |      | ASTM D792   |  |  |
| Mechanical                           | Nominal Value | Unit | Test Method |  |  |
| Tensile Strength (Break)             | 2850          | psi  | ASTM D638   |  |  |
| Tensile Elongation (Break)           | 360           | %    | ASTM D638   |  |  |
| Hardness                             | Nominal Value | Unit | Test Method |  |  |
| Durometer Hardness (Shore A, 15 sec) | 85            |      | ASTM D2240  |  |  |
| Thermal                              | Nominal Value | Unit | Test Method |  |  |
| Continuous Use Temperature           | 221           | °F   | ASTM D794   |  |  |
| Brittleness Temperature              | -18.4         | °F   | ASTM D746   |  |  |
| Flammability                         | Nominal Value | Unit | Test Method |  |  |
| Oxygen Index                         | 31            | %    | ASTM D2863  |  |  |

### **Notes**

#### Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

### Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.