

00C

## - Flexible Polyvinyl Chloride

Thursday, June 29, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	Asia Pacific			
Features	High Stiffness			
Uses	Garden Hose			
Forms	• Pellets			
Processing Method	Extrusion			

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.30		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength <sup>2</sup> (Yield)	2630	psi	ASTM D638	
Tensile Elongation <sup>2</sup> (Break)	300	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	86		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Thermal Stability <sup>3</sup> (374°F)	> 30	min	BS 2782	

## **Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 9.8 in/min

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 6/20/2016

<sup>&</sup>lt;sup>3</sup> Congo Red