

- Flexible Polyvinyl Chloride

Thursday, June 29, 2017

General Information

General

| | |
|-------------------|--|
| Material Status | • Commercial: Active |
| Availability | • Asia Pacific |
| Features | • Food Contact Acceptable • Non-Toxic |
| Uses | • Hose • Tubing |
| Forms | • Pellets |
| Processing Method | • Extrusion |

ASTM & ISO Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|------|-------------|
| Specific Gravity | 1.23 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ² (Yield) | 2630 | psi | ASTM D638 |
| Tensile Elongation ² (Break) | 300 | % | ASTM D638 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 85 | | ASTM D2240 |
| Thermal | Nominal Value | Unit | Test Method |
| Thermal Stability ³ (338°F) | > 50 | min | BS 2782 |

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min

³ Congo Red

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 1/1/2013