20

## - Polypropylene Homopolymer

Friday, June 30, 2017

General Information			
General			
Material Status	Commercial: Active		
Availability	Asia Pacific		
Filler / Reinforcement	Talc, 20% Filler by Weight		
Forms	• Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	t Test Method	
Specific Gravity	1.02		ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	8.0E-3 to 0.010	in/in	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	4640	psi	ASTM D638	
Tensile Elongation (Break)	20	%	ASTM D638	
Flexural Modulus	334000	psi	ASTM D790	
Flexural Strength	6530	psi	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	0.47	ft·lb/in	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (66 psi, Unannealed)	266	°F	ASTM D648	
Vicat Softening Temperature	307	°F	ASTM D1525 <sup>2</sup>	

## **Notes**

## **Teknor Apex Company** Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)

505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

## Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 9/26/2011

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Loading 1 (10 N)