

10

- Polypropylene Homopolymer

Friday, June 30, 2017

General Information			
General			
Material Status	Commercial: Active		
Availability	Asia Pacific		
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Forms	• Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.952		ASTM D792		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238		
Molding Shrinkage - Flow	6.0E-3	in/in	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	7250	psi	ASTM D638		
Tensile Elongation (Break)	15	%	ASTM D638		
Flexural Modulus	261000	psi	ASTM D790		
Flexural Strength	7980	psi	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	0.66	ft·lb/in	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load (66 psi, Unannealed)	311	°F	ASTM D648		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

r awtucket, renode island 02001 0.5.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 9/26/2011

¹ Typical properties: these are not to be construed as specifications.