

- Linear Low Density Polyethylene

General Information

Product Description

Sinpolene MBW1191 is a polyethylene-based pure white masterbatch designed specifically for use in tubular film blowing, blow moulding and extrusion of polyolefins. With its high pigment loading, Sinpolene MBW1191 offers high colouring value with excellent quality and performance.

The blue undertone of this masterbatch is attributed by specially selected high performance, fine crystal size rutile titanium dioxide.

Sinpolene MBW1191 is delivered as free flowing pellets for processing convenience.

CHARACTERISTICS

- * Easy processing
- * Good dispersion
- * High opacifying power
- * Excellent whiteness

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Filler / Reinforcement	• Titanium Dioxide Equivalent, 70% Filler by Weight		
Uses	• Film	• Masterbatch	• Sheet
Agency Ratings	• FDA Unspecified Rating		
Appearance	• White		
Forms	• Pellets		
Processing Method	• Blown Film	• Sheet Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.00		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20 to 60	g/10 min	ASTM D1238
Moisture Content	< 0.20	%	ASTM D3030

Additional Information

Recommended dosage: 5 - 10%

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company
Corporate Headquarters
 In U.S. for Vinyls, TPEs, Colorants,
 Engineered Thermoplastics (Chem Polymer)
 505 Central Avenue
 Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
 Fax: 401-725-8095
 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.
 Tat Bank Road
 Oldbury, West Midlands B69 4NH England
 Phone: (44) 121-665-2100
 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 7/1/2012

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.